



ZEOLITE 4A

| | |
|-------------------------------------------------------|---------------------|
| Ignition Loss (800°C 60min) | ≤ 21% |
| Ca ion exchange capacity mgCaCO ₃ /g (dry) | ≥ 310 |
| pH (suspension 1%, 25°C) | ≤ 11 |
| White grade (w=y) | ≥ 97% |
| Particle size (micron meter): | |
| -D50 (Average particle size) | 2-5μm (Average 3μm) |
| -Less than 4μm | 90% |
| -Less than 10μm | 99% |
| 325 mesh sieve residue (wet sieve) > 45μ | ≤ 0.5% |
| Al ³⁺ | ≥ 18% |
| Bulk density (g/l) | < 500 |
| Angle of repose (°) | 65 |